


Stabilisers for PVC Cables



The recommended recipes are based on IKA stabilisers, calculated on 100 phr. We are optimising the stabiliser to your specific requirements. Please contact us.

Product Form

IKA stabilisers can be delivered as powder, compacted granule or S-Granules.



Powder



Compacted Granule



S-Granules

Application 70°C

S-PVC, k-value 70		100
Plastisizer	DiDP	50
Filler		50 - 80
CaZn Stabiliser: EuroStab 3101C		3,0 - 5,0

Application 90°C/105°C

S-PVC, K-Wert 70		100
Plastisizer	DiDP	50
Filler		50 - 80
CaZn Stabilisator: EuroStab 3201C		4,0 - 8,0

Application 125°C

S-PVC, k-value 70		100
Plastisizer	TOTM	50
Filler		15 - 20
CaZn Stabilisator: EuroStab 3310C		10,0 - 14,0

P = Lead Stabilisers
C = Calcium Zinc Stabilisers
G = Compacted Granule
S = S-Granules



IKA Innovative Kunststoffaufbereitung GmbH & Co. KG

ChemiePark Bitterfeld Wolfen · Filmstraße 4 · D-06766 Bitterfeld-Wolfen · Tel.: + 49 3494 69 61-0 · Fax: + 49 3494 69 61-22
ika@ika-wolfen.de